Technical Data Sheet



Pigment Blue 15:3

General Information

Color Index	Pigment Blue 15:3 (C.I. 74160)		
Product Code	DuraPlast®3653-2		
CAS NO.	147-14-8		
EC No.	205-685-1		
Chemical Formula	C ₃₂ H ₁₆ CuN ₈		

Physical Properties

Density (g/cm³)	1.60-1.65
Specific Surface Area(m ² /g)	38-95
Oil Absorption (g/100g)	35-45
PH Value	6-8
Bulk Density (lb/gal)	13.1-14.7
Total impurities(ppm)	≤600

Fastness Properties

Heat Resistance (°C)	260	Alkali Resistance (1-5)	5
Light Resistance (Full Shade, 1-8)	7-8	Migration Resistance(1-5)	4-5
Light (Reduced tinting, 1-8)	7	Ethyl Acetate (1-5)	5
Weather Resistance (1-5)	5	Ethanol (1-5)	5
Acid Resistance (1-5)	5	MEK (1-5)	4-5

Application & Performance

Recommended for Plastic (PVC, PO, EVA), Spun fiber PP, potential used for PS, ABS.

Note

Fineland Chem offers innovative pigment technologies designed for long-lastingperformance and consistent quality in industrial use. Product data is based oncurrent knowledge and for reference only. Users should verify suitability; no liability assumed for specific applications.

Date of issue: Sept 1st, 2024

TDS Version: 2.1

Tel: +86-571-83531793 Web: www.finelandchem.com