

Technical Data Sheet

Chrome Titanium Brown



FINELAND CHEM
泛成化工

General Information

Color Index	Pigment Brown 24 (C.I. 77310)
Product Code	ColorCor®1224
CAS NO.	68186-90-3
EC No.	205-685-1
Chemical Formula	Cr-Sb-Ti-O
Hue	Yellow powder

Physical Properties

Density (g/cm ³)	4.4
Oil Absorption (g/100g)	12-22
Water soluble matter (%)	≤1.0
Mositure	≤1.0
PH Value	6-8
Sieve residue on 45 microns (%)	≤0.5
Primary particle size D50 (μm)	~1.5

Fastness Properties

Heat Resistance (°C)	<800	Alkali Resistance (1-5)	5
Light Resistance (Full Shade, 1-8)	8	Migration Resistance(1-5)	5
Light (Reduced tinting, 1-8)	8	Ethyl Acetate (1-5)	5
Weather Resistance (1-5)	5	Ethanol (1-5)	5
Acid Resistance (1-5)	5	MEK (1-5)	5

Application & Performance

Recommended for Plastic, PO, PVC (PVC & PVC Leather cloth), EVA, ABS, PS. Industrial paints, Coatings (Powder/Coil/Architectural), Fluorocarbon coating, Silicon coating, Heat resistance coating, Military camouflage coating etc. Exterior building products. Glass printing ink applications. Ceramic applications.

Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue: Sep. 1st, 2024

TDS Version: 2.1

Hangzhou Fancheng Chemical Co., Ltd.

Add: NO.776, JianSheYi Road, XiaoShan, HangZhou, ZheJiang, China.

Tel: +86-571-83531793

Web: www.finelandchem.com

Fineland Chem Co., Ltd.

Add: Room 09 27/F, Ho King Commercial Centre, 2-16 Fa Yuen Street, Mongkok, K1, HK.