

Technical Data Sheet

Pigment Brown 25



FINELAND CHEM
泛成化工

General Information

Color Index	Pigment Brown 25 (C.I. 12510)
Product Code	DuraPaint®6925-1
CAS NO.	6992-11-6
EC No.	230-258-1
Chemical Formula	<chem>C24H15Cl2N5O3</chem>

Physical Properties

Density (g/cm ³)	1.53
Specific Surface Area(m ² /g)	90
Oil Absorption (g/100g)	45-55
PH Value	6-8
Moisture Content (%)	≤1.5
Total impurities(ppm)	≤600

Fastness Properties

Heat Resistance (°C)	<290	Alkali Resistance (1-5)	5
Light Resistance (Full Shade, 1-8)	8	Bleeding Resistance(1-5)	5
Light (Reduced tinting, 1-8)	7	Ethyl Acetate (1-5)	5
Weather Resistance (1-5)	5	Ethanol (1-5)	5
Acid Resistance (1-5)	5	MEK (1-5)	5

Application & Performance

Recommended for Plastic, PO, PVC (PVC & PVC Leather cloth), EVA, Rubber, Spun Fiber-PP, also potential used in paint.

Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue: Sep. 1st , 2024

TDS Version: 2.1

Hangzhou Fancheng Chemical Co.,Ltd.

Add: NO.776, JianSheYi Road, XiaoShan, HangZhou, ZheJiang, China.

Tel: +86-571-83531793

Web: www.finelandchem.com

Fineland Chem Co., Ltd.

Add: Room 09 27/F, Ho King Commercial Centre, 2-16 Fa Yuen Street, Mongkog, KI, HK.