

# Technical Data Sheet

## Pigment Green 36



FINELAND CHEM  
泛成化工

### General Information

Color Index	Pigment Green 36 (C.I.74265)
Product Code	DuraPaint®3736
CAS NO.	14302-13-7
EC No.	238-238-4
Chemical Formula	C <sub>32</sub> Br <sub>6</sub> Cl <sub>10</sub> CuN <sub>8</sub>

### Physical Properties

Density (g/cm <sup>3</sup> )	2.31-3.19
Specific Surface Area(m <sup>2</sup> /g)	30-64
Oil Absorption (g/100g)	35-45
PH Value	6-8
Bulk Density (lb/gal)	12.0-12.5
Total impurities(ppm)	≤600

### Fastness Properties

Heat Resistance (°C)	280	Alkali Resistance (1-5)	5
Light Resistance (Full Shade, 1-8)	7-8	Migration Resistance(1-5)	5
Light (Reduced tinting, 1-8)	7	Ethyl Acetate (1-5)	4-5
Weather Resistance (1-5)	5	Ethanol (1-5)	5
Acid Resistance (1-5)	5	MEK (1-5)	5

### Application & Performance

Recommended for Industrial paint, Coil coating, Powder coating, Decorative water/solvent-base paint, Automotive Refinish paint etc.

### Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue: Sep 1<sup>st</sup>, 2024

TDS Version: 2.1

Hangzhou Fancheng Chemical Co., Ltd.  
Add: NO.776, JianSheYi Road, XiaoShan, HangZhou, ZheJiang, China.  
Tel: +86-571-83531793  
Web: www.finelandchem.com

Fineland Chem Co., Ltd.  
Add: Room 09 27/F, Ho King Commercial Centre, 2-16 Fa Yuen Street, Mongkok, K1, HK