Technical Data Sheet



Cobalt Titanate Green

(-oporal	Intormation
	Information

Color Index	Pigment Green 50 (C.I. 77377)
Product Code	ColorCor®1750
CAS NO.	68186-85-6
EC No.	269-047-4
Chemical Formula	Co-Ni-Zn-Al-O
Hue	Green powder

Physical Properties

Density (g/cm³)	4.2
Oil Absorption (g/100g)	10-20
Water soluble matter (%)	≤1.0
Mositure	≤1.0
PH Value	7-9.5
Sieve residue on 45 microns (%)	≤0.5
Primary particle size D50 (μm)	~1.5

Fastness Properties

Heat Resistance (°C)	<800
Light Resistance (Full Shade, 1-8)	8
Light (Reduced tinting, 1-8)	8
Weather Resistance (1-5)	5
Acid Resistance (1-5)	5

Alkali Resistance (1-5)	5
Migration Resistance(1-5)	5
Ethyl Acetate (1-5)	5
Ethanol (1-5)	5
MEK (1-5)	5

Application & Performance

Recommended for Plastic, PO, PVC (PVC & PVC Leather cloth), EVA, ABS, PS. Industrial paints, Coatings (Powder/Coil/Architectural), Fluorocarbon coating, Silicon coating, Heat resistance coating, Military camouflage coating etc. Exterior building products. Glass printing ink applications. Ceramic applications.

Note

Fineland Chem offers innovative pigment technologies designed for long-lastingperformance and consistent quality in industrial use. Product data is based oncurrent knowledge and for reference only. Users should verify suitability; no liability assumed for specific applications.

Date of issue: Sep. 1st, 2024

TDS Version: 2.1