

Technical Data Sheet

Pigment Green 7



FINELAND CHEM
泛成化工

General Information

Color Index	Pigment Green 7 (C.I. 74260)
Product Code	DuraPaint®S6707
CAS NO.	1328-53-6
EC No.	215-524-7
Chemical Formula	C ₃₂ Cl ₁₆ CuN ₈

Physical Properties

Density (g/cm ³)	1.55-2.05
Specific Surface Area(m ² /g)	40-80
Oil Absorption (g/100g)	35-45
PH Value	6.0-8.0
Bulk Density (lb/gal)	15.0-20.5
Total impurities(ppm)	≤600

Fastness Properties

Heat Resistance (°C)	260	Alkali Resistance (1-5)	5
Light Resistance (Full Shade, 1-8)	8	Migration Resistance(1-5)	5
Light (Reduced tinting, 1-8)	7	Ethyl Acetate (1-5)	5
Weather Resistance (1-5)	5	Ethanol (1-5)	5
Acid Resistance (1-5)	5	MEK (1-5)	5

Application & Performance

Recommended for Industrial paint, Coil coating, Powder coating, Decorative water/solvent-base paint, Automotive Refinish paint etc.

Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue Sep. 1st, 2024

TDS Version 2.1

Hangzhou Fancheng Chemical Co., Ltd.
Add NO.776, JianSheYi Road, XiaoShan, HangZhou, ZheJiang,
China.
Tel: +86-571-83531793
Web: www.finelandchem.com

Fineland Chem Co., Ltd.
Add Room 09 27/F, Ho King Commercial Centre, 2-16 Fa
Yuen Street, Mongkok, K1, HK