

Technical Data Sheet

Pigment Orange 13



FINELAND CHEM
泛成化工

General Information

Color Index	Pigment Orange 13 (C.I. 21110)
Product Code	DuraPlast®3213
CAS NO.	3520-72-7
EC No.	222-530-3
Chemical Formula	C ₃₂ H ₂₄ Cl ₂ N ₈ O ₂

Physical Properties

Density (g/cm ³)	1.31-1.60
Specific Surface Area(m ² /g)	35-42
Oil Absorption (g/100g)	35-45
PH Value	6.5-7.5
Bulk Density (lb/gal)	10.9-13.36
Total impurities(ppm)	≤600

Fastness Properties

Heat Resistance (°C)	200	Alkali Resistance (1-5)	3
Light Resistance (Full Shade, 1-8)	4-5	Migration Resistance(1-5)	3-4
Light (Reduced tinting, 1-8)	4	Ethyl Acetate (1-5)	3
Weather Resistance (1-5)	2-3	Ethanol (1-5)	3
Acid Resistance (1-5)	3	MEK (1-5)	3

Application & Performance

Recommended for Plastic (PVC, PE, PP, Rubber, EVA).

Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue: Sep. 1st, 2024

TDS Version: 2.1

Hangzhou Fancheng Chemical Co., Ltd.
Add: NO.776, JianSheYi Road, XiaoShan, HangZhou, ZheJiang, China.
Tel: +86-571-83531793
Web: www.finelandchem.com

Fineland Chem Co., Ltd.
Add: Room 09 27/F, Ho King Commercial Centre, 2-16 Fa Yuen Street, Mongkok, K1, HK.