

Technical Data Sheet

Pigment Orange 16



FINELAND CHEM
泛成化工

General Information

Color Index	Pigment Orange 16 (C.I.21160)
Product Code	DuraPlast® 6516
CAS NO.	6505-28-8
EC No.	229-388-1
Chemical Formula	C ₃₄ H ₃₂ N ₆ O ₆

Physical Properties

Density (g/cm ³)	1.28-1.51
Specific Surface Area(m ² /g)	-
Oil Absorption (g/100g)	28-54
PH Value	6-8
Bulk Density (lb/gal)	10.6-12.5
Total impurities(ppm)	≤600

Fastness Properties

Heat Resistance (°C)	180	Alkali Resistance (1-5)	4
Light Resistance (Full Shade, 1-8)	6	Migration Resistance(1-5)	3-4
Light (Reduced tinting, 1-8)	5	Ethyl Acetate (1-5)	4
Weather Resistance (1-5)	4	Ethanol (1-5)	5
Acid Resistance (1-5)	4	MEK (1-5)	4

Application & Performance

Recommended for inks, paints & coating (Decorative, OEM, industrial, powder) etc.

Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue: Sep 1st, 2024

TDS Version: 2.1

Hangzhou Fancheng Chemical Co., Ltd.
Add: NO.776, JianSheYi Road, XiaoShan, HangZhou, ZheJiang, China.
Tel: +86-571-83531793
Web: www.finelandchem.com

Fineland Chem Co., Ltd.
Add: Room 09 27/F, Ho King Commercial Centre, 2-16 Fa Yuen Street, Mongkok, K1, HK