# **Technical Data Sheet**



#### **Iron Oxide**

Gan	oral	l ni	orm	ation
4				[- 4 6]

Color Index	Pigment Red 101 (C.I. 77492)
Product Code	DuraPlast®3130M
CAS NO.	51274-00-1
EC No.	257-098-5
Chemical Formula	α-Fe <sub>2</sub> O <sub>3</sub>

## **Physical Properties**

Contents Fe <sub>2</sub> O <sub>3</sub> (%)	≥86
Oil Absorption (g/100g)	35-45
Res.on 325 mesh(%)	≤0.3
Water soluble matter(%)	≤1.0
Moisture(%)	≤1.5
PH Value	6-8
Bulk density(g/cm³)	5.5

### **Fastness Properties**

Heat Resistance (°C):	300
Light Resistance (Full Shade, 1-8):	8
Light (Reduced tinting, 1-8)	8
Weather Resistance (1-5):	5
Acid Resistance (1-5):	4

Alkali Resistance (1-5):	4
Migration Resistance(1-5)	5
Ethyl Acetate (1-5)	4
Ethanol (1-5)	4
MEK (1-5)	4

## **Application & Performance**

Recommended for Building materials, concrete, bricks, paints & coatings, fertilizers, plastics and rubber polymers, fiber cement, paper, mortar, wood plastic composites, paving tiles, industrial coatings, roof tiles, ceramic products.

#### Note

Fineland Chem offers innovative pigment technologies designed for long-lastingperformance and consistent quality in industrial use. Product data is based oncurrent knowledge and for reference only. Users should verify suitability; no liability assumed for specific applications.

Date of issue: Sep. 1st, 2024

TDS Version: 2.1

Web: www.finelandchem.com

China. Tel: +86-571-83531793