

Technical Data Sheet

Pigment Red 149



FINELAND CHEM
泛成化工

General Information

Color Index	Pigment Red 149 (C.I. 71137)
Product Code	DuraPlast® 3549
CAS NO.	4948-15-6
EC No.	225-590-9
Chemical Formula	C ₄₀ H ₂₆ N ₂ O ₄

Physical Properties

Density (g/cm ³)	1.29-1.3
Specific Surface Area(m ² /g)	59
Oil Absorption (g/100g)	45-50
PH Value	6-7
Bulk Density (lb/gal)	11.7
Total impurities(ppm)	≤600

Fastness Properties

Heat Resistance (°C)	300	Alkali Resistance (1-5)	5
Light Resistance (Full Shade, 1-8)	8	Bleeding Resistance(1-5)	5
Light (Reduced tinting, 1-8)	7	Ethyl Acetate (1-5)	5
Weather Resistance (1-5)	5	Ethanol (1-5)	5
Acid Resistance (1-5)	5	MEK (1-5)	5

Application & Performance

Recommended for Plastic, PO, PVC(PVC & PVC Leather cloth), EVA, ABS, Spun Fiber-PP/PET/Nylon.

Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue Sep. 1st, 2024

TDS Version 2.1

Hangzhou Fancheng Chemical Co., Ltd.
Add NO.776, JianSheYi Road, XiaoShan, HangZhou, ZheJiang,
China.
Tel: +86-571-83531793
Web: www.finelandchem.com

Fineland Chem Co., Ltd.
Add Room 09 27/F, Ho King Commercial Centre, 2-16 Fa
Yuen Street, Mongkok, K1, HK