

Technical Data Sheet

Pigment Red 169



FINELAND CHEM
泛成化工

General Information

Color Index	Pigment Red 169 (C.I. 45160:2)
Product Code	DuraPrint® 6569
CAS NO.	12237-63-7
EC No.	235-469-2
Chemical Formula	C ₂₈ H ₃₁ N ₂ O ₃

Physical Properties

Density (g/cm ³)	1.47-2.20
Specific Surface Area(m ² /g)	89-92
Oil Absorption (g/100g)	40-50
PH Value	6-9
Moisture Content(%)	≤2.5
Total impurities(ppm)	≤600

Fastness Properties

Heat Resistance (°C)	160	Alkali Resistance (1-5)	4
Light Resistance (Full Shade, 1-8)	5-6	Bleeding Resistance(1-5)	3-4
Light (Reduced tinting, 1-8)	5	Ethanol (1-5)	3
Weather Resistance (1-5)	3	Ethanol (1-5)	3
Acid Resistance (1-5)	4	MEK (1-5)	2

Application & Performance

Recommended for Water based ink.

Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue Sep. 1st, 2024

TDS Version 2.1

Hangzhou Fancheng Chemical Co., Ltd.
Add NO.776, JianSheYi Road, XiaoShan, HangZhou, ZheJiang,
China.
Tel: +86-571-83531793
Web: www.finelandchem.com

Fineland Chem Co., Ltd.
Add Room 09 27/F, Ho King Commercial Centre, 2-16 Fa
Yuen Street, Mongkok, K1, HK