

Technical Data Sheet

Pigment Red 254



FINELAND CHEM
泛成化工

General Information

Color Index	Pigment Red 254 (C.I. 56110)
Product Code	DuraPlast®3524-3S
CAS NO.	84632-65-5
EC No.	402-400-4
Chemical Formula	<chem>C18H10Cl2N2O2</chem>

Physical Properties

Density (g/cm ³)	1.49
Specific Surface Area(m ² /g)	30.40
Oil Absorption (g/100g)	49.10
PH Value	6.5-7.5
Moisture Content (%)	≤1.5
Total impurities(ppm)	≤600

Fastness Properties

Heat Resistance (°C)	300	Alkali Resistance (1-5)	5
Light Resistance (Full Shade, 1-8)	8	Bleeding Resistance(1-5)	5
Light (Reduced tinting, 1-8)	7	Ethyl Acetate (1-5)	5
Weather Resistance (1-5)	5	Ethanol (1-5)	5
Acid Resistance (1-5)	5	MEK (1-5)	4-5

Application & Performance

Recommended for Plastic, paints and printing inks. Excellent all-around properties, high color strength and brilliant high performance middle red organic pigment.

Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue Sep 1st , 2024

TDS Version 2.1