

Technical Data Sheet

Cerium Sulfide Red



FINELAND CHEM
泛成化工

General Information

Color Index	Pigment Red 275 (C.I. 772830)
Product Code	ColorCor®1575
CAS NO.	12014-93-6
EC No.	-
Chemical Formula	Ce ₂ S ₃
Hue	Red powder

Physical Properties

Density (g/cm ³)	3.5
Oil Absorption (g/100g)	30-40
Water soluble matter (%)	≤1.0
Mositure	≤1.0
PH Value	7-9
Sieve residue on 45 microns (%)	≤0.5
Primary particle size D50 (μm)	~3

Fastness Properties

Heat Resistance (°C)	<300	Alkali Resistance (1-5)	4
Light Resistance (Full Shade, 1-8)	8	Migration Resistance(1-5)	5
Light (Reduced tinting, 1-8)	8	Ethyl Acetate (1-5)	5
Weather Resistance (1-5)	5	Ethanol (1-5)	5
Acid Resistance (1-5)	3	MEK (1-5)	5

Application & Performance

Recommended for Plastic, PO, PVC (PVC & PVC Leather cloth), EVA, ABS, PS. Industrial paints, Coatings (Powder/Coil/Architectural) Exterior building products etc. It is an excellent substitute for heavy metal inorganic pigments such as Cadmium red.

Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue: Sep. 1st, 2024

TDS Version: 2.1