

Technical Data Sheet

Pigment Red 48:2



FINELAND CHEM
泛成化工

General Information

Color Index	Pigment Red 48:2 (C.I. 15865:2)
Product Code	DuraPlast®3582H
CAS NO.	7023-61-2
EC No.	230-303-5
Chemical Formula	C ₁₈ H ₁₁ CLN ₂ O ₆ SCa

Physical Properties

Density (g/cm ³)	1.5
Specific Surface Area(m ² /g)	45-56
Oil Absorption (g/100g)	40-60
PH Value	6-8
Moisture Content (%)	≤2.0
Total impurities(ppm)	≤600

Fastness Properties

Heat Resistance (°C)	230	Alkali Resistance (1-5)	3-4
Light Resistance (Full Shade, 1-8)	5	Migration Resistance (1-5)	5
Light (Reduced tinting, 1-8)	4	Ethyl Acetate (1-5)	4
Weather Resistance (1-5)	3	Ethanol (1-5)	4
Acid Resistance (1-5)	5	MEK (1-5)	3

Application & Performance

Recommended for plastic(PO,PVC,Rubber,EVA),also for Spun fiber PP.

Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue: Sep., 1st 2024

TDS Version: 2.1

Hangzhou Fancheng Chemical Co.,Ltd.
Add: NO.776, JianSheYi Road, XiaoShan, HangZhou,
ZheJiang, China.
Tel: +86-571-83531793
Web: www.finelandchem.com

Fineland Chem Co., Ltd.
Add: Room 09 27/F, Ho King Commercial Centre,
2-16 Fa Yuen Street, Mongkogh, KI, HK