Technical Data Sheet



Pigment Red 57:1

General Information

Color Index	Pigment Red 57:1 (15850:1)		
Product Code	DuraPrint®W6571B		
CAS NO.	5281-04-9		
EC No.	226-109-5		
Chemical Formula	$C_{18}H_{12}N_2O_6SCa$		

Physical Properties

Density (g/cm³)	1.42-1.80
Specific Surface Area(m²/g)	68
Oil Absorption (g/100g)	40-50
PH Value	6-9
Bulk Density (lb/gal)	11.8-14.9
Total impurities(ppm)	≤600

Fastness Properties

Heat Resistance ($^{\circ}$ C)	180	Alkali Resistance (1-5):	4
Light Resistance (Full Shade, 1-8)	4-5	Migration Resistance(1-5)	4
Light (Reduced tinting, 1-8)	4	Ethanol (1-5)	4
Weather Resistance (1-5)	3-4	Ethyl Acetate (1-5)	4
Acid Resistance (1-5)	4	MEK (1-5)	3

Application & Performance

Recommended for water based ink, bluish shade, high color strength.

Note

Fineland Chem offers innovative pigment technologies designed for long-lastingperformance and consistent quality in industrial use. Product data is based oncurrent knowledge and for reference only. Users should verify suitability; no liability assumed for specific applications.

Date of issue: Sep. 1st, 2024

TDS Version: 2.1

Tel: +86-571-83531793 Web: www.finelandchem.com