

Technical Data Sheet

Pigment Red 8 Dispersion



FINELAND CHEM
泛成化工

General Information

Color Index	Pigment Red 8 (C.I. 12335)
Product Code	HueMaster®5508
CAS NO.	6410-30-6
EC No.	229-100-4
Chemical Formula	C ₂₄ H ₁₇ ClN ₄ O ₄
Appearance	Red Liquid

Physical Properties

Pigment Content	Approx. 40%
Total Solid Content	Approx. 42%-43%
Fineness	5µm max
PH Value	6-9
Viscosity	1800mpa.s

Fastness Properties

Heat Resistance (°C)	160	Alkali Resistance (1-5)	4
Light Resistance (Full Shade, 1-8)	4-5	Migration Resistance(1-5)	4
Light (Reduced tinting, 1-8)	4	Ethanol (1-5)	4
Weather Resistance (1-5)	4	Ethyl Acetate (1-5)	3
Acid Resistance (1-5)	4	MEK (1-5)	3

Application & Package

Recommended for Paint, Coating, Printing ink, Textile printing, Agricultural applications (Fertilizer, Pesticide, Seeds etc.)

Pacage: 20kg/30kg Plastic Drum

Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue Sep 1st, 2024

TDS Version 2.1

Hangzhou Fancheng Chemical Co.,Ltd.
Add NO.776, JianSheYi Road, XiaoShan, HangZhou,
ZheJiang, China.
Tel +86-571-83531793
Web: www.finelandchem.com

Fineland Chem Co., Ltd.
Add Room 09 27/F, Ho King Commercial Centre, 2-16
Fa Yuen Street, Mongkok, K1, HK