

Technical Data Sheet

Pigment Violet 23



FINELAND CHEM
泛成化工

General Information

Color Index	Pigment Violet 23 (C.I. 51319)
Product Code	DuraPlast®S6023-1B
CAS NO.	215247-95-3
EC No.	606-790-9
Chemical Formula	C ₃₄ H ₂₂ Cl ₂ N ₄ O ₂

Physical Properties

Density (g/cm ³)	1.4-1.6
Specific Surface Area(m ² /g)	65-100
Oil Absorption (g/100g)	35-45
PH Value	5.5-8
Moisture Content (%)	≤1.5
Total impurities(ppm)	≤600

Fastness Properties

Heat Resistance (°C)	240	Alkali Resistance (1-5)	5
Light Resistance (Full Shade, 1-8)	7	Migration Resistance(1-5)	5
Light (Reduced tinting, 1-8)	6	Ethanol (1-5)	5
Weather Resistance (1-5)	5	Ethyl Acetate (1-5)	4
Acid Resistance (1-5)	5	MEK (1-5)	5

Application & Performance

Recommended for solvent-based ink, low viscosity, bluish shade.

Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue: Sep. 1st, 2024

TDS Version: 2.1

Hangzhou Fancheng Chemical Co.,Ltd.
Add: NO.776, JianSheYi Road, XiaoShan, HangZhou,
ZheJiang, China.
Tel: +86-571-83531793
Web: www.finelandchem.com

Fineland Chem Co., Ltd.
Add: Room 09 27/F, Ho King Commercial Centre, 2-16
Fa Yuen Street, Mongkok, K1, HK.