

Technical Data Sheet

Zinc Ferrites Yellow



FINELAND CHEM
泛成化工

General Information

Color Index	Pigment Yellow 119 (C.I. 77496)
Product Code	ColorCor®1119
CAS NO.	68187-51-9
EC No.	269-103-8
Chemical Formula	Zn-Fe-O
Hue	Yellow powder

Physical Properties

Density (g/cm ³)	5.0
Oil Absorption (g/100g)	40-50
Water soluble matter (%)	≤1.0
Mositure	≤1.0
PH Value	5-8
Sieve residue on 45 microns (%)	≤0.5
Primary particle size D50 (μm)	~1.5

Fastness Properties

Heat Resistance (°C)	<600	Alkali Resistance (1-5)	5
Light Resistance (Full Shade, 1-8)	8	Migration Resistance(1-5)	5
Light (Reduced tinting, 1-8)	8	Ethyl Acetate (1-5)	5
Weather Resistance (1-5)	5	Ethanol (1-5)	5
Acid Resistance (1-5)	5	MEK (1-5)	5

Application & Performance

Recommended for Plastic, PO, PVC (PVC & PVC Leather cloth), EVA, ABS, PS. Industrial paints, Coatings (Powder/Coil/Architectural), Fluorocarbon coating, Silicon coating, Heat resistance coating, Military camouflage coating etc. Exterior building products..

Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue: Sep. 1st, 2024

TDS Version: 2.1