

# Technical Data Sheet

## Pigment Yellow 139



FINELAND CHEM  
泛成化工

### General Information

Color Index	Pigment Yellow 139 (C.I.56298)
Product Code	DuraPaint®6139
CAS NO.	36888-99-0
EC No.	253-256-2
Chemical Formula	C <sub>16</sub> H <sub>9</sub> N <sub>5</sub> O <sub>6</sub>

### Physical Properties

Density (g/cm <sup>3</sup> )	1.74
Specific Surface Area(m <sup>2</sup> /g)	22-25
Oil Absorption (g/100g)	35-45
PH Value	5-6
Bulk Density (lb/gal)	10-15
Total impurities(ppm)	≤600

### Fastness Properties

Heat Resistance (°C)	200	Alkali Resistance (1-5)	5
Light Resistance (Full Shade, 1-8)	7-8	Bleeding Resistance(1-5)	5
Light (Reduced tinting, 1-8)	7	Ethyl Acetate (1-5)	5
Weather Resistance (1-5)	4	Ethanol (1-5)	5
Acid Resistance (1-5)	5	MEK (1-5)	5

### Application & Performance

Recommended for Industrial paint, Coil coating, Powder coating, Decorative water/solvent-base paint, Automotive Refinish paint etc.

### Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue: Sep. 1<sup>st</sup>, 2024

TDS Version: 2.1

Hangzhou Fancheng Chemical Co., Ltd.  
Add: NO.776, JianSheYi Road, XiaoShan, HangZhou, ZheJiang, China.  
Tel: +86-571-83531793  
Web: www.finelandchem.com

Fineland Chem Co., Ltd.  
Add: Room 09 27/F, Ho King Commercial Centre, 2-16 Fa Yuen Street, Mongkok, K1, HK.