

Technical Data Sheet

Pigment Yellow 14



FINELAND CHEM
泛成化工

General Information

Color Index	Pigment Yellow 14 (C.I. 21095)
Product Code	DuraPlast®T3188-1
CAS NO.	5468-75-7
EC No.	226-789-3
Chemical Formula	C ₃₄ H ₃₀ CL ₂ N ₆ O ₄

Physical Properties

Density (g/cm ³)	1.14-1.52
Specific Surface Area(m ² /g)	35
Oil Absorption (g/100g)	35-35
PH Value	6-8
Moisture Content (%)	≤2.0
Total impurities(ppm)	≤600

Fastness Properties

Heat Resistance (°C)	200	Alkali Resistance (1-5)	4
Light Resistance (Full Shade, 1-8)	5-6	Migration Resistance(1-5)	3
Light (Reduced tinting, 1-8)	5	Ethyl Acetate (1-5)	4
Weather Resistance (1-5)	3-4	Ethanol (1-5)	4
Acid Resistance (1-5)	4	MEK (1-5)	3

Application & Performance

Recommended for Plastic(PVC,PE,PP,Rubber,EVA). also used in water based system.It's the high color strength and high purity Y14.

Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue: Sep., 1st 2024

TDS Version: 2.1

Hangzhou Fancheng Chemical Co.,Ltd.
Add: NO.776, JianSheYi Road, XiaoShan, HangZhou,
ZheJiang, China.
Tel: +86-571-83531793
Web: www.finelandchem.com

Fineland Chem Co., Ltd.
Add: Room 09 27/F, Ho King Commercial Centre, 2-16
Fa Yuen Street, Mongkok, KI, HK