

# Technical Data Sheet

## Pigment Yellow 150



FINELAND CHEM  
泛成化工

### General Information

Color Index	Pigment Yellow 150 (C.I. 12764)
Product Code	DuraPlast®3150F
CAS NO.	25157-64-6
EC No.	270-944-8
Chemical Formula	C <sub>8</sub> H <sub>6</sub> N <sub>6</sub> O <sub>6</sub> NI

### Physical Properties

Density (g/cm <sup>3</sup> )	1.80-1.90
Specific Surface Area(m <sup>2</sup> /g)	110-130
Oil Absorption (g/100g)	40-60
PH Value	6.5-7.5
Bulk Density (lb/gal)	17-17.3
Total impurities(ppm)	≤600

### Fastness Properties

Heat Resistance (°C)	270	Alkali Resistance (1-5)	5
Light Resistance (Full Shade, 1-8)	7-8	Bleeding Resistance(1-5)	5
Light (Reduced tinting, 1-8)	7	Ethyl Acetate (1-5)	5
Weather Resistance (1-5)	4-5	Ethanol (1-5)	5
Acid Resistance (1-5)	5	MEK (1-5)	5

### Application & Performance

Recommended for Fiber, Spun Fiber-PP/PET.

### Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue Sep. 1<sup>st</sup>, 2024

TDS Version 2.1

Hangzhou Fancheng Chemical Co., Ltd.  
Add NO.776, JianSheYi Road, XiaoShan, HangZhou, ZheJiang,  
China.  
Tel: +86-571-83531793  
Web: www.finelandchem.com

Fineland Chem Co., Ltd.  
Add Room 09 27/F, Ho King Commercial Centre, 2-16 Fa  
Yuen Street, Mongkok, K1, HK