

Technical Data Sheet

Pigment Yellow 154



FINELAND CHEM
泛成化工

General Information

Color Index:	Pigment Yellow 154 (C.I. 11781)
Product Code:	DuraPaint®6154
CAS NO.:	68134-22-5
EC No.:	268-734-6
Chemical Formula:	C ₁₈ H ₁₄ F ₃ N ₅ O ₃

Physical Properties

Density (g/cm ³)	1.57
Specific Surface Area(m ² /g)	18
Oil Absorption (g/100g)	61
PH Value	6-8
Bulk Density (lb/gal)	13.3
Total impurities(ppm)	≤600

Fastness Properties

Heat Resistance (°C)	200	Alkali Resistance (1-5)	4-5
Light Resistance (Full Shade, 1-8)	7-8	Bleeding Resistance(1-5)	5
Light (Reduced tinting, 1-8)	7	Ethyl Acetate (1-5)	3-4
Weather Resistance (1-5)	4-5	Ethanol (1-5)	4
Acid Resistance (1-5)	5	MEK (1-5)	3-4

Application & Performance

Recommended for Industrial paint, Coil coating, Powder coating, Decorative water/solvent-base paint, Automotive Refinish paint etc.

Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue: Sep.1st, 2024

TDS Version: 2.1

Hangzhou Fancheng Chemical Co., Ltd.
Add: NO.776, JianSheYi Road, XiaoShan, HangZhou, ZheJiang, China.
Tel: +86-571-83531793
Web: www.finelandchem.com

Fineland Chem Co., Ltd.
Add: Room 09 27/F, Ho King Commercial Centre, 2-16 Fa Yuen Street, Mongkok, K1, HK