

Technical Data Sheet

Pigment Yellow 3



FINELAND CHEM
泛成化工

General Information

Color Index	Pigment Yellow 3 (C.I. 11710)
Product Code	DuraPaint®6103
CAS NO.	6486-23-3
EC No.	299-355-1
Chemical Formula	C ₁₆ H ₁₂ Cl ₂ N ₄ O ₄

Physical Properties

Density (g/cm ³)	1.35-1.45
Specific Surface Area(m ² /g)	6.8-12
Oil Absorption (g/100g)	35-45
PH Value	5.0-8.0
Moisture Content (%)	≤2.0
Total impurities(ppm)	≤600

Fastness Properties

Heat Resistance (°C)	160	Alkali Resistance (1-5)	5
Light Resistance (Full Shade, 1-8)	5-6	Bleeding Resistance(1-5)	3
Light (Reduced tinting, 1-8)	5	Ethyl Acetate (1-5)	4
Weather Resistance (1-5)	3-4	Ethanol (1-5)	3-4
Acid Resistance (1-5)	5	MEK (1-5)	4

Application & Performance

Recommended for Industrial paint, Decorative water/solvent-base paint etc.

Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue Sep. 1st, 2024

TDS Version 2.1

Hangzhou Fancheng Chemical Co., Ltd.
Add NO.776, JianSheYi Road, XiaoShan, HangZhou,
ZheJiang, China.
Tel: +86-571-83531793
Web: www.finelandchem.com

Fineland Chem Co., Ltd.
Add Room 09 27/F, Ho King Commercial Centre, 2-16
Fa Yuen Street, Mongkok, K1, HK