

Technical Data Sheet

Pigment Yellow 34



FINELAND CHEM
泛成化工

General Information

Color Index	Pigment Yellow 34 (C.I.19140)
Product Code	DuraPaint®C6134D
CAS NO.	1344-37-2
EC No.	215-693-7
Chemical Formula	<chem>PbCrO4+PbSO4</chem>

Physical Properties

Density (g/cm ³)	4.5
Specific Surface Area(m ² /g)	4
Oil Absorption (g/100g)	28-30
PH Value	4-8
Moisture Content (%)	≤1.5
Total impurities(ppm)	≤600

Fastness Properties

Heat Resistance (°C)	<230	Alkali Resistance (1-5)	4
Light Resistance (Full Shade, 1-8)	5-6	Bleeding Resistance(1-5)	5
Light (Reduced tinting, 1-8)	5	Ethyl Acetate (1-5)	5
Weather Resistance (1-5)	3-4	Ethanol (1-5)	5
Acid Resistance (1-5)	4	MEK (1-5)	5

Application & Performance

Recommended for Industrial paint, Coil coating, Powder coating, Road marking, Decorative water/solvent-base paint etc, also used for Plastics/Rubber.

Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue: Sep 1st , 2024

TDS Version: 2.1

Hangzhou Fancheng Chemical Co.,Ltd.

Add: NO.776, JianSheYi Road, XiaoShan, HangZhou, ZheJiang, China.

Tel: +86-571-83531793

Web: www.finelandchem.com

Fineland Chem Co., Ltd.

Add: Room 09 27/F, Ho King Commercial Centre, 2-16 Fa Yuen Street, Mongkog, KI, HK