

Technical Data Sheet

Pigment Yellow 74



FINELAND CHEM
泛成化工

General Information

Color Index	Pigment Yellow 74 (C.I. 11741)
Product Code	DuraPaint®6174T
CAS NO.	6358-31-2
EC No.	228-768-4
Chemical Formula	C ₁₈ H ₁₈ N ₄ O ₆

Physical Properties

Density (g/cm ³)	1.28-1.51
Specific Surface Area(m ² /g)	45
Oil Absorption (g/100g)	35-45
PH Value	6-8
Moisture Content (%)	≤1.5
Total impurities(ppm)	≤600

Fastness Properties

Heat Resistance (°C)	180	Alkali Resistance (1-5)	5
Light Resistance (Full Shade, 1-8)	6-7	Bleeding Resistance(1-5)	4
Light (Reduced tinting, 1-8)	6	Ethyl Acetate (1-5)	3
Weather Resistance (1-5)	3-4	Ethanol (1-5)	4
Acid Resistance (1-5)	5	MEK (1-5)	4

Application & Performance

Recommended for Industrial paint, Decorative water/solvent-base paint etc. It's transparent .

Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue: Sep. 1st , 2024

TDS Version: 2.1

Hangzhou Fancheng Chemical Co.,Ltd.
Add: NO.776, JianSheYi Road, XiaoShan, HangZhou,
ZheJiang, China.
Tel: +86-571-83531793
Web: www.finelandchem.com

Fineland Chem Co., Ltd.
Add: Room 09 27/F, Ho King Commercial Centre, 2-16
Fa Yuen Street, Mongkok, K1, HK