

# Technical Data Sheet

## Pigment Yellow 83



FINELAND CHEM  
泛成化工

### General Information

Color Index:	Pigment Yellow 83 (C.I. 21108)
Product Code:	DuraPlast®3183F
CAS NO.:	5567-15-7
EC No.:	226-939-8
Chemical Formula:	C <sub>36</sub> H <sub>32</sub> Cl <sub>4</sub> N <sub>6</sub> O <sub>8</sub>

### Physical Properties

Density (g/cm <sup>3</sup> )	1.27-1.50
Specific Surface Area(m <sup>2</sup> /g)	49
Oil Absorption (g/100g)	39-45
PH Value	6-7.5
Moisture Content (%)	≤1.5
Total impurities(ppm)	≤600

### Fastness Properties

Heat Resistance (°C)	220	Alkali Resistance (1-5)	5
Light Resistance (Full Shade, 1-8)	6-7	Migration Resistance(1-5)	5
Light (Reduced tinting, 1-8)	6	Ethyl Acetate (1-5)	4
Weather Resistance (1-5)	4	Ethanol (1-5)	4
Acid Resistance (1-5)	5	MEK (1-5)	4

### Application & Performance

Recommended for Plastic, EVA with good dispersion.

### Note

Finland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue: Sep. 1<sup>st</sup>, 2024

TDS Version: 2.1

Hangzhou Fancheng Chemical Co.,Ltd.  
Add: NO.776, JianSheYi Road, XiaoShan, HangZhou,  
ZheJiang, China.  
Tel: +86-571-83531793  
Web: www.finelandchem.com

Fineland Chem Co., Ltd.  
Add: Room 09 27/F, Ho King Commercial Centre, 2-16  
Fa Yuen Street, Mongkok, K1, HK