

Technical Data Sheet

Solvent Blue 36



FINELAND CHEM
泛成化工

General Information

Color Index	Solvent Blue 36
Product Code	CorSol®3636
CAS NO.	14233-37-5
EC No.	903-150-3
Chemical Formula	C ₂₀ H ₂₂ N ₂ O ₂

Physical Properties

Bulk Density (g/cm ³)	0.31
Melting point(°C)	176
Moisture(%)	≤0.5
Ash(%)	≤0.3
Insolubility(%)	≤0.3
PH Value	6-8
Insolubility(%)	≤1000

Fastness Properties

Heat Resistance (°C) in PS	280	Migration Resistance(1~5)	5
Light Resistance (Full Shade, 1~8)	6-7	Resistance to Acid(1~5)	4
Light (Reduced tinting, 1~8)	6	Resistance to Alkali(1~5)	5

*Heat Resistance: the maximum temperature in °C at which minutes in the barrel of an injection molding machine as a change of color (DE ≤ 3) occurs after a dwell time of 5per DIN EN 12877-1.

Application & Performance

Recommended for plastic,PS, HIPS, RPVC, PMMA, SAN, polymer, fiber, rubber, gasoline, oil, lubricants, wax, candle etc.

Note

*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

Date of issue: Sep. 1st , 2024

TDS Version: 2.1

Hangzhou Fancheng Chemical Co.,Ltd.

Add: NO.776, JianSheYi Road, XiaoShan, HangZhou, ZheJiang, China.

Tel: +86-571-83531793

Web: www.finelandchem.com

Fineland Chem Co., Ltd.

Add: Room 09 27/F, Ho King Commercial Centre, 2-16 Fa Yuen Street, Mongkog, KI, HK