

Technical Data Sheet

Solvent Blue 97



FINELAND CHEM
泛成化工

General Information

Color Index	Solvent Blue 97(C.I.615290)
Product Code	CorSol®3697
CAS NO.	32724-62-2
EC No.	251-178-3
Chemical Class	Anthraquinone
Hue	Reddish Blue

Physical Properties

Bulk Density (g/cm ³)	0.73
Melting point (°C)	approx. 200
Moisture(%)	≤0.5
Ash(%)	≤0.3
Insolubility(%)	≤0.3
PH Value	6-8
Fe Content(ppm)	≤1000

Fastness Properties

Heat Resistance (°C) in PS	300	Migration Resistance(1~5)	5
Light Resistance (Full Shade, 1-8)	7	Resistance to Acid(1~5)	5
Light (Reduced tinting, 1~8)	6	Resistance to Alkali(1~5)	5

*Heat Resistance: the maximum temperature in °C at which a change of color (DE ≤ 3) occurs after a dwell time of 5 minutes in the barrel of an injection molding machine as per DIN EN 12877-1.

Application & Performance

Recommended for Plastic (PS, SAN, PMMA, PC, PET, PA6, ABS and ABS/PC blends), potential to use in PA66.

Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue: Sep., 1st 2024

TDS Version: 2.1

Hangzhou Fancheng Chemical Co., Ltd.

Add: NO.776, JianSheYi Road, XiaoShan, HangZhou, Zhejiang, China.

Tel: +86-571-83531793

Web: www.finelandchem.com

Fineland Chem Co., Ltd.

Add: Room 09 27/F, Ho King Commercial Centre, 2-16 Fa Yuen Street, Mongkok, K1, HK