

Technical Data Sheet

SPC PY191



General Information

Color Index	Pigment Yellow 191 (C.I. 18795)
Product Code	DuraPlast®SPC3191
CAS NO.	129423-54-7
EC No.	403-530-4
Chemical Formula	C ₁₇ H ₁₃ CaClN ₄ O ₇ S ₂

Physical Properties

Pigment Concentration	50%
Appearance	Granular flakes
Density (g/cm ³)	1.7-1.8
PH Value	5.0-7.5
Bulk Density (lb/gal)	3-5
Total impurities(ppm)	≤600

Fastness Properties

Heat Resistance (°C)	300	Alkali Resistance (1-5)	5
Light Resistance (Full Shade, 1-8)	7-8	Bleeding Resistance(1-5)	5
Light (Reduced tinting, 1-8)	6-7	Ethyl Acetate (1-5)	4
Weather Resistance (1-5)	4	Ethanol (1-5)	4
Acid Resistance (1-5)	5	MEK (1-5)	4

Application & Performance

Recommended for Plastic(PO, PVC, EVA),Also use in PS,ABS.

Note

Fineland Chem offers innovative pigment technologies designed for long-lasting performance and consistent quality in industrial use. Product data is based on current knowledge and for reference only. Users should verify suitability; no liability is assumed for specific applications.

Date of issue Sep. 1st, 2024

TDS Version 2.1