

Technical Data Sheet

Ultramarine Blue



FINELAND CHEM
泛成化工

General Information

Color Index	Pigment Blue 29 (C.I. 77007)
Product Code	DuraPaint®6629
CAS NO.	57455-37-5
EC No.	611-533-9
Chemical Formula	Ultramarine

Physical Properties

Oil Absorption (g/100g)	35-45
Res.on 325 mesh(%)	≤0.3
Water soluble matter(%)	≤1.0
Moisture(%)	≤1.5
PH Value	7-9
Free Sulphur(%)	≤0.05

Fastness Properties

Heat Resistance (°C):	350	Alkali Resistance (1-5):	5
Light Resistance (Full Shade, 1-8):	8	Migration Resistance(1-5)	5
Light (Reduced tinting, 1-8)	7	Ethyl Acetate (1-5)	4
Weather Resistance (1-5):	5	Ethanol (1-5)	4
Acid Resistance (1-5):	1-2	MEK (1-5)	4

Application & Performance

Recommended for Building materials, Paints & Coatings, Fertilizers, Plastics and Rubber, Stationary and Art pastes etc.

Note

*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

Date of issue: Sep. 1st, 2024

TDS Version: 2.1

Hangzhou Fancheng Chemical Co.,Ltd.
Add: NO.776, JianSheYi Road, XiaoShan, HangZhou,
ZheJiang, China.
Tel: +86-571-83531793
Web: www.finelandchem.com

Fineland Chem Co., Ltd.
Add: Room 09 27/F, Ho King Commercial Centre, 2-16
Fa Yuen Street, Mongkok, KI, HK.