

Technical Data Sheet

Pigment Red 169



FINELAND CHEM
泛成化工

General Information

Color Index	Pigment Red 169 (C.I. 45160:2)
Product Code	DuraPrint®6569
CAS NO.	12237-63-7
EC No.	235-469-2
Chemical Formula	C ₂₈ H ₃₁ N ₂ O ₃

Physical Properties

Density (g/cm ³)	1.47-2.20
Specific Surface Area(m ² /g)	89-92
Oil Absorption (g/100g)	40-50
PH Value	6-9
Bulk Density (lb/gal)	12.2-18.3
Total impurities(ppm)	≤600

Fastness Properties

Heat Resistance (°C)	160	Alkali Resistance (1-5)	4
Light Resistance (Full Shade, 1-8)	5-6	Bleeding Resistance(1-5)	3-4
Light (Reduced tinting, 1-8)	5	Ethanol (1-5)	3
Weather Resistance (1-5)	3	Ethanol (1-5)	3
Acid Resistance (1-5)	4	MEK (1-5)	2

Application & Performance

Recommended for Water based ink.

Note

*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

Date of issue Sep. 1st, 2024

TDS Version 2.1

Hangzhou Fancheng Chemical Co.,Ltd.
Add NO.776, JianSheYi Road, XiaoShan, HangZhou,
ZheJiang, China.
Tel: +86-571-83531793
Web: www.finelandchem.com

Fineland Chem Co., Ltd.
Add Room 09 27/F, Ho King Commercial Centre, 2-16
Fa Yuen Street, Mongkok, KI, HK