Technical Data Sheet



Solvent Blue 35

| | | | e e | |
|------|------|----|------|--------|
| (ien | eral | In | torn | nation |

| Color Index | Solvent Blue 35(C.I.61554) |
|----------------|----------------------------|
| Product Code | CorSol®3635 |
| CAS NO. | 17354-14-2 |
| EC No. | 241-379-4 |
| Chemical Class | Anthraquinone |
| Hue | Bright Greenish Blue |

Physical Properties

| Bulk Density (g/cm³) | 0.7-0.8 |
|----------------------|-----------------|
| Melting point (°C) | approx. 108-112 |
| Moisture(%) | ≤0.5 |
| Ash(%) | ≤0.3 |
| Insolubility(%) | ≤0.3 |
| PH Value | 6-8 |
| Fe Content(ppm) | ≤1000 |

Fastness Properties

| Heat Resistance (°C) in PS | | Migration Resistance(1~5) | 5 |
|---------------------------------------|---|---------------------------|---|
| Light Resistance (Full Shade, 1-8) 6- | | Resistance to Acid(1~5) | 5 |
| Light (Reduced tinting, 1~8) | 6 | Resistance to Alkali(1~5) | 5 |

^{*}Heat Resistance: the maximum temperature in $^{\circ}$ C at which a change of color (DE \leq 3) occurs after a dwell time of 5 minutes in the barrel of an injection molding machine as per DIN EN 12877-1.

Application & Performance

Recommended for Plastic (PS, SAN, PMMA, PC, ABS and ABS/PC blends).

Note

*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

Date of issue: Sep., 1st 2024

TDS Version: 2.1

Tel: +86-571-83531793 Web: www.finelandchem.com