

Technical Data Sheet

Pigment Yellow 184



FINELAND CHEM
泛成化工

General Information

Color Index	Pigment Yellow 184 (C.I.771740)
Product Code	ColorCor®C6184
CAS NO.	14059-33-7
EC No.	237-898-0
Chemical Formula	Bismuth Vanadate

Physical Properties

Density (g/cm ³)	6.2
Oil Absorption (g/100g)	23-33
Water soluble matter (%)	≤1.0
Mositure	≤1.0
PH Value	6-8
Sieve residue on 45 microns (%)	≤0.5
Primary particle size D50 (μm)	~0.2

Fastness Properties

Heat Resistance (°C)	<270	Alkali Resistance (1-5)	5
Light Resistance (Full Shade, 1-8)	8	Migration Resistance(1-5)	5
Light (Reduced tinting, 1-8)	7	Ethyl Acetate (1-5)	5
Weather Resistance (1-5)	5	Ethanol (1-5)	5
Acid Resistance (1-5)	5	MEK (1-5)	5

Application & Performance

Recommended for PlasticIndustrial paint,Coil coating,Powder coating,Decorative water/solvent-base paint,Automotive Refinish paint etc.Also used for Ink and Silicone products.

Note

*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

Date of issue: Sep. 1st, 2024

TDS Version: 2.1