

Technical Data Sheet

Solvent Violet 36



FINELAND CHEM
泛成化工

General Information

Color Index	Solvent Violet 36(C.I.)
Product Code	CorSol®3036
CAS NO.	61951-89-1
EC No.	/
Chemical Class	Anthraquinone
Hue	Reddish Violet

Physical Properties

Bulk Density (g/cm ³)	0.6
Melting point (°C)	approx.213
Moisture(%)	≤0.5
Ash(%)	≤0.3
Insolubility(%)	≤0.3
PH Value	6-8
Fe Content(ppm)	≤1000

Fastness Properties

Heat Resistance (°C) in PS	300	Migration Resistance(1~5)	5
Light Resistance (Full Shade, 1-8)	6	Resistance to Acid(1~5)	5
Light (Reduced tinting, 1~8)	5	Resistance to Alkali(1~5)	5

*Heat Resistance: the maximum temperature in °C at which a change of color (DE ≤ 3) occurs after a dwell time of 5 minutes in the barrel of an injection molding machine as per DIN EN 12877-1.

Application & Performance

Recommended for Plastic (PS, SAN,PMMA,PC,PET,PA6,ABS and ABS/PC blends).

Note

*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

Date of issue: Sep., 1st 2024

TDS Version: 2.1