

Technical Data Sheet

Pigment Red 146



FINELAND CHEM
泛成化工

General Information

Color Index	Pigment Red 146 (C.I. 12485)
Product Code	DuraPrint®6148-1
CAS NO.	5280-68-2
EC No.	226-103-2
Chemical Formula	C ₃₃ H ₂₇ ClN ₄ O ₆

Physical Properties

Density (g/cm ³)	1.35-1.40
Specific Surface Area(m ² /g)	36-40
Oil Absorption (g/100g)	60-70
PH Value	7-8
Moisture Content (%)	≤2
Total impurities(ppm)	≤600

Fastness Properties

Heat Resistance (°C)	200	Alkali Resistance (1-5)	5
Light Fastness (Full Shade, 1-8)	6-7	Bleeding Resistance(1-5)	5
Light (Reduced tinting, 1-8)	6	Ethanol (1-5)	4
Weather Resistance (1-5)	4-5	Ethyl Acetate (1-5)	4
Acid Resistance (1-5)	5	MEK (1-5)	4

Application & Performance

Recommended for millbase, ink(solvent-based ink, water-based ink) and coating (Decorative, industrial).Bluish shade.

Note

*Product specific and application information are based upon our current knowledge. They are non-binding and cannot be taken as guarantee. Users must establish the suitability of individual products. We do not accept any liability relating to the use of our products in particular applications.

Date of issue Sep. 1st, 2024

TDS Version 2.1

Hangzhou Fancheng Chemical Co.,Ltd.
Add NO.776, JianSheYi Road, XiaoShan, HangZhou,
ZheJiang, China.
Tel: +86-571-83531793
Web: www.finelandchem.com

Fineland Chem Co., Ltd.
Add Room 09 27/F, Ho King Commercial Centre, 2-16
Fa Yuen Street, Mongkoko, KI, HK